

Telf. 902 929 084 Web: <http://www.niberma.com> E-mail: info@niberma.es

## FICHA TÉCNICA PAVIMENTO GRABOFLEX 251/T 4,4 MM

### 1. Technical specifications

**Issued by:** Graboplast Floor Covering Manufacturers Ltd.

**Purpose:** Technical data determining the quality of floorcovering in rolls conforming to GPHSZ-038

### 2. Main characteristics

**Designations:** sports-flooring, with moderate flame spread on flameproof concrete subfloor

**Film:** PVC

### 3. Technical Data of the Product

Parameter	Specification	Tolerance	Test method
Thickness mm	<b>4,4</b>	+ - 0,2	MSZ EN 428
Linear change in dimensions % - length	<b>+ - 0,2</b>	max.	MSZ EN 434
Residual indentation mm	<b>0,35</b>	max.	MSZ EN 433
Peel resistance N/50mm - length	<b>50</b>	min.	MSZ EN 431
Peel resistance N/50mm - cross	<b>50</b>	min.	MSZ EN 431
Colour-fastness to light	<b>6</b>	min.	MSZ EN 20105 B02. 3m
Chemical resistance - 50% ethyl alcohol contact time 120 min	<b>no change</b>	appr.	MSZ EN 423
Chemical resistance - 5% fatty alcohol sulphonate contact time 120 min	<b>no change</b>	appr.	MSZ EN 423
Chemical resistance - 5% acetic acid contact time 120 min	<b>no change</b>	appr.	MSZ EN 423
Chemical resistance - petrol contact time 120 min	<b>no change</b>	appr.	MSZ EN 423
Wear layer thickness mm	<b>0,7</b>	min.	MSZ EN 429
Width cm	<b>200</b>	min.	MSZ EN 426

### 4. Informative data

Parameter	Specification	Tolerance	Test method
Weight g/m <sup>2</sup>	<b>2890</b>	kb	MSZ EN 430

**Valid from:**  
2005.06.28.

**Approved by:**  
Reményi István Leader of Quality  
Management